



# Technical Bulletin

2400 Boston Street, Suite 200, Baltimore, Maryland 21224  
Phone: 410-675-2100 or 800-543-3840

Revised: 01/30/03

## DAP® KWIK FOAM® Polyurethane Insulating Sealant

- Fills, seals and insulates
- Prevents energy loss
- Helps stop drafts and pests
- Waterproof
- Minimal expanding

**Packaging:** 12 ounces (340 grams,) 24 ounces (680 grams)

**Color:** Creamy Yellow

**UPC Number:** 18230, 18232, 74200, 74202, 74204

### Company Identification:

Manufacturer: DAP Inc., 2400 Boston St., Baltimore, Maryland 21224

Usage Information: DAP HELPLINE: 888-DAP-TIPS, 9:00 am to 7:00 pm EST.

Order Information: 800-327-3339

Fax Number: 410-534-2650

Also, visit the DAP website at [www.dap.com](http://www.dap.com).

### Product Description:

DAP ®KWIK FOAM® Insulating Foam Sealant is a one-component, moisture cure, polyurethane insulating foam that expands to economically fill and seal large cavities. It expands to form a permanent, waterproof bond to wood, concrete, metal, glass and brick. It stops air infiltration and will not shrink or degrade. Contains a flame retardant and meets Montreal Protocol 1987, Vienna Protocol 1986 and Bill 218 of the Province of Ontario, Canada. Cured foam can be sanded, painted or stained.

### Suggested Uses:

KWIK FOAM® is ideal for sealing around pipes, ducts, vents, electrical outlets and cables. It can be used for filling large gaps and cracks in foundations, masonry walls, crawlspaces and more. It provides an insulating seal to wood, concrete, brick, vinyl, steel and aluminum. Applications include homes, RV's, mobile homes, campers and boats. **NOT RECOMMENDED FOR USE IN FILLING ENCLOSED CAVITIES (BETWEEN WALLS OR UNDER TUB SURROUNDS).** May cause jambs or sills to buckle.

### Performance Characteristics:

- KWIK FOAM® is formulated to expand 2 1/2 - 3 times the contents of the can to fill and seal large leaks, gaps, and holes. DAP® KWIK FOAM® is a minimal expanding foam sealant when compared to other polyurethane insulating foam sealants.
- Tack free in 20 minutes. Fully expanded in 1 hour. Fully cured in 24 hours. (Cure times vary based on bead size, temperature and humidity.)
- UL Classified – file #R-13919 Caulking and Sealants Surface Burning Characteristics Applied to Inorganic Reinforced Cement Board:

Flame Spread	20
Smoke Developed	70

### **Surface Preparation & Application:**

1. Wear safety glasses with side shields and gloves. Use in well-ventilated areas. All areas not to be foamed should be covered with masking tape or dropcloths
2. Clean and remove grease, dirt and debris from application area.
3. Apply at temperatures between 65°F – 100° F.
4. Screw trigger nozzle into valve. Shake can for one minute before use.
5. Familiarize yourself with the foam by practicing on newspapers. Gauge expansion by allowing test bead to expand for 60 minutes.
6. Moisten substrate for filling cavities greater than 3” diameter.
7. With valve end of can down, pull trigger slowly to dispense foam. Dispense foam into lower part of cavity first and fill to only 40% to leave room for expansion. **DO NOT DISTURB FRESHLY DISPENSED FOAM.**
8. Cured foam exposed to sunlight must be coated with paint or stain.
9. If storing to re-use, leave nozzle on valve. When ready to re-use, cut off one inch of nozzle tip and re-shake the can for one minute. Use remainder of can within 30 days.

**PRECAUTIONARY MEASURES FOR USE, HANDLING, STORAGE AND DISPOSAL:** Use in a well-ventilated area. Do not get on eyes or skin. Do not breathe vapors. Wear gloves and eye protection with side shields. Do not puncture or incinerate can. Do not expose to heat or store above 120°F. Do not place in hot water or near radiators, stoves or other sources of heat. Do not keep can in direct sunlight or high temperature areas, such as automobiles. If exposed to heat or direct sunlight, container may explode. Store in a cool dry place. Use only as directed. This product is combustible and may constitute a fire hazard if improperly used. **DO NOT USE NEAR OPEN FLAME.** Cured foam may be combustible if exposed to flame or temperatures above 240°F. If burned, cured foam may release hazardous decomposition products. For additional information refer to the Material Safety Data Sheet.

### **Physical & Chemical Characteristics:**

Color:	Creamy Yellow
Consistency:	Foam
Vehicle:	Isocyanate Prepolymer
Flash Point:	N/A
Propellant:	Hydrogenated Chlorofluoroalkane
Specific Gravity:	1.2
Shelf Life:	18 months
Weight/Gallon:	13.40 ± 0.05 lbs./gal.
Service Temperature:	200°F
Application Temperature:	65°F – 100°F
MSDS No:	77005
Insulation Rating:	R5 per inch
Coverage:	235 linear feet or 1/3 – 1/2 cubic feet

### **Clean Up:**

Uncured foam can be cleaned up with paint thinner or acetone. Cured foam cannot be removed with solvents. Excess cured foam can be removed by trimming with a sharp knife. **DO NOT** use acetone or other solvents to remove product from skin. **SKIN CONTACT:** Wipe excess uncured foam off with a paper towel immediately. Wash remaining uncured foam immediately with soap and water. Remaining uncured residue can be removed with petroleum jelly or baby oil. For cured foam, soak in warm soapy water, then apply petroleum jelly. Cured foam will wear off in time.

**Safety:**

See product label or Material Safety Data Sheet for safety information. You can request an MSDS sheet by calling 888-DAP-TIPS or by visiting our website at [www.dap.com](http://www.dap.com).

**Satisfaction Guaranteed:**

If not satisfied with product's performance when used as directed, return used container and sales receipt to DAP Inc., Technical Customer Service, 2400 Boston St., Baltimore, MD, 21224, for product replacement or sales price refund. DAP will not be liable for incidental or consequential damage.